

Stamping Volumeter

STV 2003

Principle

Measurement of stamping volume and stamping density.

Manufacturer	THG Wolfgang Glock KG
Revolution speed	250 min ⁻¹ ±15
Drop height of the stemp	3 mm ± 0.1mm
Counter	up to 3000 hits
Use of measuring cylinder	25 to 1000 ml
